

EPOSYST SL

Pigmented two-component solvent-free epoxy resin flooring system of wide use

Total thickness ≥ 1,5-3 mm

Uses production sites, assembly halls, warehouses, storage halls, workshops, offices, corridors, garages, agricultural facilities, airplane hangars, archives

FeRFA type 4/5

Consumption ca:

Primer	EPOKATE KRUNT, transparent, EP, 2-component, solvent- and nonylphenol free	0,3-0,4 kg/m ²
---------------	--	---------------------------



broad casting

Fire dried silica sand ø 0,1-0,3 mm

0,8-1,0 kg/m²

Optional / Scratch primer up to 1 mm depth of roughness:

Scratch primer (optional)	EPOKATE KRUNT, transparent, EP, 2-component, solvent- and nonylphenol free	0,6-0,8 kg/m ²
----------------------------------	--	---------------------------



filler

Fire dried silica sand ø 0,1-0,3 mm

0,2-0,25 kg/m²



broad casting

Fire dried silica sand ø 0,1-0,8 mm

0,8-1,0 kg/m²

Self-levelling coat	EPOKATE SL, pigmented, EP, 2-component solvent- and nonylphenol free, glossy	1,5-1,6 kg/m ² /mm
----------------------------	--	-------------------------------



filler (optional)

Fire dried silica sand ø 0,1-0,3 mm

0-0,8 kg/m²/mm