

## EPOSYST SL/R

Pigmented two-component solvent-free epoxy resin flooring system with slip resistance surface

**Total thickness**  $\geq 2\text{-}3\text{ mm}$

**Uses** **wet process production sites, warehouses, storage halls, beverage industry, maintenance workshops, storage halls, washrooms and garages, corridors, loading ramps, agricultural facilities, offices, corridors, garages, agricultural facilities, storage rooms**

**FeRFA type 5**

Consumption ca:

**Primer** EPOKATE KRUNT, transparent, EP, 2-component, solvent- and nonylphenol free 0,3-0,4 kg/m<sup>2</sup>



broad casting Fire dried silica sand  $\varnothing 0,1\text{-}0,3\text{ mm}$  0,8-1,0 kg/m<sup>2</sup>

Optional / Scratch primer up to 1 mm depth of roughness:

*Scratch primer (optional)* EPOKATE KRUNT, transparent, EP, 2-component, solvent- and nonylphenol free 0,6-0,8 kg/m<sup>2</sup>



filler Fire dried silica sand  $\varnothing 0,1\text{-}0,3\text{ mm}$  0,2-0,25 kg/m<sup>2</sup>



broad casting Fire dried silica sand  $\varnothing 0,1\text{-}0,8\text{ mm}$  0,8-1,0 kg/m<sup>2</sup>

**First layer** EPOKATE SL, pigmented, EP, 2-component solvent- and nonylphenol free, glossy 1,0 kg/m<sup>2</sup>



filler (optional) Fire dried silica sand  $\varnothing 0,1\text{-}0,3\text{ mm}$  0-0,5 kg/m<sup>2</sup>



antislip scatter Fire dried silica sand  $\varnothing 0,4\text{-}0,8\text{ mm}$  2,5 kg/m<sup>2</sup>

**Top coat** EPOKATE SL, pigmented, EP, 2-component solvent- and nonylphenol free, glossy 0,8 kg/m<sup>2</sup>